



PINE CHEMICAL GROUP

PRODUCT DATA SHEET – BLEACHED SOFTWOOD KRAFT PULP (BSKP - UTL)

General Information

BSKP-UTL:
TU

Bleached softwood kraft pulp
5411-003-80255613-2007 rev.1-5

Specification of BSKP-BRT

Properties	Standard for grades
	Super Extra
1. Beating characteristics at 60 SR (PFI mill)	
Breaking length, km , not less than	9,0
Tear Index, mN*m ² /g, not less than	8,5
2. Brightness, %, not less than	89,0
3. pH at cold extraction	5,5-7,0
4. Dirt over 0,1mm ² , pcs, not more than	5
5. Humidity, %, not more than	20
6. Estimated humidity, %	10

In all applications of **BSKP-UTL** it is the sole responsibility of the buyer to respect and comply with any valid intellectual property rights of third parties.

