



PINE CHEMICAL GROUP

**PRODUCT DATA SHEET – SULFATE UNBLEACHED SOFTWOOD PULP FLASH
DRIED
(SUSP_{FD} - UTL)**

General Information

**SUSP_{fd}-UTL:
TU**

Sulfate unbleached softwood pulp flash dried
5411-005-80255613-2007 rev.1-2

Specification of SUSP_{fd} -UTL

Properties	Standard
Breaking length, km , not less than	9
Tear Index, mN*m ² /g, not less than	8.5
Index bursting, kPa*m ² /g, not less than	6
Dirtiness, over 5 mm ² , pieces, not more than	100
Delignification degree, Kappa	18-50
Humidity, %, not more than	20
Estimated Humidity, %, not more than	10

In all applications of **SUSP_{fd} -UTL** it is the sole responsibility of the buyer to respect and comply with any valid intellectual property rights of third parties.

